



Protecta AS
Kjetil Bogstad
Ravneveien 7
3174 Revetal
Norway

Eurofins Product Testing A/S
Smedeskovvej 38
DK-8464 Galten
Denmark

Tel. +45 70 22 42 76
Fax +45 70 22 42 75
voc@eurofins.dk
www.eurofins.com/product-emissions

Date
1 March 2012

Your ref.
-

Our ref.
G13688D/Rev/IB

Test Report – LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)

Sample material

Sample identification	Protecta EX Gipsmørtel
Product type	Sealant
Product data, according to manufacturer	Density: 1.0 g/cm ^{3**} Water content: 0 g/l*** Exempt compounds***
Date received	2 February 2012
Analytical period	February 2012

Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty
LEED 2009 EQ c4.1 ASTM D 2369 - 10	Gravimetric	Total Volatiles, SCAQMD rule 304	1 g/l	10 %

Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of double testing.

The backing paper has been removed from the self-adhesive label material prior the testing.

U_m (%): The expanded uncertainty U_m is equal to 2 x RSD%, see also www.eurofins.dk, keyword: Måleusikkerhed

Analytical results

	Solid content, % mass	Water content, % mass	Exempt com- pounds, % mass	VOC less wa- ter less ex- empt com- pounds, g/l	VOC limit g/l
Protecta EX Gipsmørtel	99	0***	0***	10	420*

* VOC limit for "Other Sealants".

** Given by the client.

*** No information about water content and exempt compounds. Set to zero.

This amended report replaces the previous report. The VOC limit has been corrected.

Eurofins Product Testing A/S

Inge Bondgaard
Chemical engineer, Head of customer centre